




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B22D 17/10, 25/00	A1	(11) International Publication Number: WO 00/43152 (43) International Publication Date: 27 July 2000 (27.07.00)
(21) International Application Number: PCT/US99/30322 (22) International Filing Date: 20 December 1999 (20.12.99) (30) Priority Data: 09/238,405 26 January 1999 (26.01.99) US (71) Applicant: SPX CORPORATION [US/US]; 700 Terrace Point Drive, Muskegon, MI 49443 (US). (72) Inventor: DASGUPTA, Rathindra; 7109 Hickory Point Drive, Portage, MI 49024 (US). (74) Agent: TIMMONS, Stephen, D.; Hovey, Williams, Timmons & Collins, Suite 400, 2405 Grand Boulevard, Kansas City, MO 64108 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: ALLOY FOR SEMI-SOLID CASTING PROCESS  (57) Abstract <p>A semi-solid casting process uses 390 aluminum alloy as the preferred casting alloy (18) for producing castings (20) with high wear resistance.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

ALLOY FOR SEMI-SOLID CASTING PROCESS

5

10

15

BACKGROUND OF THE INVENTION

1. FIELD OF THE INVENTION

20

The present invention relates to the field of metal casting. In particular, the invention is concerned with a semi-solid casting process using an aluminum alloy.

2. DESCRIPTION OF THE PRIOR ART

25

The use of aluminum in the automotive industry, has become more important with the increased need for weight reduction. Aluminum, however, is soft and various aluminum alloys with better wear resistance characteristics have been developed for use as a casting material.

30

One of these alloys is 390 aluminum alloy which has been used for automotive components requiring high wear resistance. As those skilled in the art are aware, the use of 390 aluminum alloy, however, presents handling problems. For example, to achieve the desired microstructure for high wear resistance, this alloy is normally cast in molten form with a reagent added to

prevent clustering of the primary silicon particles. The nature of the semi-solid process is such that addition of reagents is not necessary, as the casting material is semi-solid and not molten.

5 SUMMARY OF THE INVENTION

The present invention solves the prior art problems discussed above and provides a distinct advance in the state of the art. In particular, the casting process hereof enables the use of 390 aluminum alloy in the semi-solid casting process.

The preferred method in accordance with the present invention includes the steps of producing a slug of aluminum alloy from an MHD or grain refined billet, heating the slug to a predetermined semi-solid temperature and maintain the temperature for a predetermined time, injecting the slug into a mold cavity to form a casting therein, and then removing the casting from the cavity. In the preferred embodiment these steps are performed without adding a reagent to the slug and the preferred alloy is 390 aluminum alloy. Other preferred aspects of this present invention are described herein.

20 BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is the sole drawing figure and is a schematic illustration of the preferred semi-solid casting apparatus using a slug of 390 aluminum alloy for implementing the preferred method in accordance with the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Fig. 1 schematically illustrates conventional semi-solid casting apparatus 10 for implementing the preferred method in accordance with the present invention. Apparatus 10 includes hydraulic cylinder or ram 12 and mold 14 defining mold cavity 16 therein. In operation, ram 12 injects semi-solid slug 18 into cavity 16 to form casting 20 therein. Casting 20 is then removed from mold 14 and cooled.

In the preferred embodiment, slug 18 is composed of 390 aluminum alloy or the equivalent thereof. Specifically, 390 aluminum alloy includes:

5 silicon between about 16.0 and 18.0%(by weight),
 iron less than about 0.40 %,
 copper between about 4.0 and 5.0%,
 manganese less than about 0.10%,
 magnesium between about 0.50 and 0.65%,
10 nickel less than about 0.10%,
 zinc less than about 0.05%,
 titanium less than about 0.20%,
 lead and tin less than about 0.03%,
 with the remainder of alloy being aluminum.

15 Slug 18 is produced by cutting from an MHD or grain refined billet. Such a billet presents the desired microstructure to produce casting 20. Other methods may also be used to produce slug 18, but this is the most common method in use today. The volume of slug 18 is predetermined and substantially equal to the volume of finished casting 20.

20 After cutting slug 18 from the billet, slug 18 is heated to about 567°C (predetermined semi-solid temperature) using heating equipment for semi-solid casting. At the semi-solid temperature, slug 18 is solid enough to retain its shape but is sufficiently soft to flow into cavity 16 and take the shape thereof in order to form casting 20 during the semi-solid casting process:

25 In the prior art, it has been required to add a reagent to 390 aluminum alloy along with other chemical agents before casting while the material is in the molten state in order to achieve the desired microstructure of the finished casting. In the semi-solid process, a reagent or other chemicals cannot be added to slug 18 because of its semi-solid state.

30 Contrary to the prior art, however, it has been discovered by the inventor hereof that a slug 18 of 390 aluminum alloy can be heated to the semi-solid temperature without significantly losing the desired microstructure as presented in the billet from which the slug was cut. Moreover, it has been discovered that the slug 18, at the semi-solid temperature, can be injected into
35 mold cavity 16 of semi-solid casting apparatus 10 without significantly losing

the desired microstructure in the resulting casting 20. Using the preferred method hereof, casting 20 presents a tensile strength between about 51 and 57 ksi and an elongation of less than about 1% after the casting undergoes preferred heat treatment procedure T6 consisting of solution treatment at 496°C for eight hours, water quenched, and then artificially aged at 176°C for five hours followed by conventional cooling. Finally, it has been discovered that the semi-solid process can be used without abnormal wear on mold 14.

Those skilled in the art will now appreciate that the present invention enables the production of wear resistant, aluminum alloy castings using the semi-solid casting process with all of the attendant benefits of the semi-solid casting process. It will also be appreciated that the present invention encompasses many variations in the preferred embodiment described herein. For example, some deviation can occur in the specified ranges for the chemical components of the preferred 390 aluminum alloy without substantially defecting the quality of the resulting casting. Also, other heat treatment procedures can be used. Having thus described the preferred embodiment, the following is claimed as new and desired to be secured by Letters Patent:

CLAIMS:

1. In a semi-solid casting process in which a slug of an alloy is heated to a semi-solid temperature and injected into a mold cavity to form a casting therein, the improvement comprising:

injecting an aluminum alloy as said alloy, said aluminum alloy including

silicon between about 16.0 and 18.0%,

iron less than about 0.40 %,

copper between about 4.0 and 5.0%,

manganese less than about 0.10%,

magnesium between about 0.50 and 0.65%,

nickel less than about 0.10%,

zinc less than about 0.05%,

titanium less than about 0.20%,

lead and tin less than about 0.03%,

with the remainder of said alloy being aluminum.

2. The improvement as set forth in claim 1, said aluminum alloy including 390 aluminum alloy.

3. A method of making a casting comprising:
- (a) producing a slug of selected size from a billet of an aluminum alloy having a desired microstructure;
- (b) heating said slug to a predetermined semi-solid temperature and maintaining said temperature for a predetermined time;
- (c) in a semi-solid casting process, injecting said slug into a mold cavity to form a casting therein; and
- (d) removing said casting from said cavity and allowing said casting to cool,

said method further including the step of performing steps (a) - (c) without adding a reagent to said slug,

said aluminum alloy including

silicon between about 16.0 and 18.0%,

iron less than about 0.40 %,

copper between about 4.0 and 5.0%,

manganese less than about 0.10%,

magnesium between about 0.50 and 0.65%,

nickel less than about 0.10%,

zinc less than about 0.05%,

titanium less than about 0.20%,


lead and tin less than about 0.03%,

with the remainder of said alloy being aluminum.

4. The method of claim 3, step (b) including the step of heating said slug to a temperature between about 565°C and 580°C.

5. The method of claim 3, step (b) including step of maintaining said semi-solid temperature for between about 10 and 20 minutes.

6. The method of claim 3, said method including the step of making one of a steering component, crank shaft hub, compressor piston, swash plate, and transmission oil housing as said casting.

*Fig. 1.*

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US99/30322

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :B22D 17/10, 25/00

US CL :164/113

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 164/76.1, 113, 476, 900; 148/549

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
WEST

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,846,350 A (BERGSMA) 08 December 1998, col. 6, lines 34-67; col. 9, lines 56-62; col. 10, lines 43-54; col. 12, lines 42-49 and col. 12, line 66 through col. 13, line 3.	1-6

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
B earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

03 MARCH 2000

Date of mailing of the international search report

14 APR 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

KUANG Y LIN

Telephone No. (703) 308-0661

DEBORAH THOMAS
PARALEGAL SPECIALIST